

## MANUFACTURE OF METALLIZED SYNTHETIC FIBER STAPLE

Patent Number: JP60021912  
Publication date: 1985-02-04  
Inventor(s): HIRAOKA SABUROU; others: 02  
Applicant(s): MITSUBISHI RAYON KK  
Requested Patent: ☐ JP60021912

Application Number: **JP19830126910 19830714**

Priority Number(s):

IPC Classification: D01G1/00; C23C14/20; D06M11/00

EC Classification:

EC Classification:

Equivalents:

---

### Abstract

---

**PURPOSE:** To obtain the titled staple having excellent antistaticity and antibacterial property, by flattening a continuous synthetic fiber tow, metallizing the surface of the tow with a metal having electrical conductivity and antibacterial property, cutting the tow in the form of staples, and mixing the staples.

**CONSTITUTION:** A continuous tow of a synthetic fiber, preferably an acrylic fiber, free from a textile lubricant is flattened to a thickness of  $\leq 0.5$  mm, preferably  $\leq 0.3$  mm, with a tow creel and a drawing roller. One or both surfaces of the flattened tow are metallized with a metal having electrical conductivity and/or antibacterial property (e.g. Al) with a vacuum-metallizing device, and the metallized tow is cut to staples and mixed.

---

Data supplied from the **esp@cenet** database - 12